### elcometer

### **Elcometer 3086 Motorised Pencil Hardness Tester**



Elcometer 3086 Motorised Pencil Hardness Tester

Can be used in accordance with: ASTM D 3363 BS 3900-E19 ECCA T4 EN 13523-4 ISO 15184 JIS K 5600-5-4

Standards in grey have been superceded but are still recognised in some industries.

Traditional pencil hardness testers can be limited in their reproducibility and repeatability by two key factors; the uniformity of the carriage speed and the variation of the applied force by the user as the manual tester is moved across the coating.

The Elcometer 3086 Motorised Pencil Hardness Tester, using the same test methods and principles as the Elcometer 501 pencil hardness tester, removes both of these variables by being fully independent. The internal motor drives the unit at a constant. uniform speed across the coated surface. exertina fixed. а user determined force between 0 - 10N (0 -2.25lbF).

Using the pencil lead holder, pencil leads of varying hardness values can be quickly interchanged to determine a coating's hardness rating.

Manufactured from anodised aluminium, the Elcometer 3086 can travel forwards (chip method) or backwards (indentation method), as required. Hardness Testing Hardness can be defined as a material's resistance to permanent deformation.

In the coatings industry, hardness measurement can be used to determine the resistance of the coating to scratching from general wear and tear and also if a coating is fully cured.

The term "Hardness" is used to refer to different properties of material, specifically:

Resistance to scratch and wear Resistance to penetration

Depending on the requirements, there are various methods for testing hardness. Some are dedicated to characterise coatings and others are more suitable for testing bulk materials such as metals, plastics, rubber or elastomers.

| TECHNICAL SPECIFICATION |  |  |  |  |
|-------------------------|--|--|--|--|
| Dimensions              | 280 x 140 x 240mm (11 x 5.5 x 9.4")  |  |  |  |
| Weight                  | 3.8kg (8.4lb)  |  |  |  |
| Part Number             | K0UK3086M001 Elcometer 3086 Motorised Pencil Hardness Tester, UK 240V                          |  |  |  |
|                         | K0003086M001 Elcometer 3086 Motorised Pencil Hardness Tester, EUR 220V                         |  |  |  |
|                         | K0US3086M001 Elcometer 3086 Motorised Pencil Hardness Tester, US 110V                          |  |  |  |
| Packing List            | Elcometer 3086, lead holder, lead set (14 cases of leads, grades 6H to 6B, 12 leads per case), |  |  |  |
|                         | positioning block, abrasive sharpener, abrasive paper and operating instructions               |  |  |  |

# data sheet


## elcometer

| ACCESSORIES            |              |                        |              |
|------------------------|--------------|------------------------|--------------|
| Spare Lead Holder      |              |                        | KT003084P220 |
| 12 Hardness Leads (6B) | KT003084P001 | 12 Hardness Leads (F)  | KT003084P008 |
| 12 Hardness Leads (5B) | KT003084P002 | 12 Hardness Leads (H)  | KT003084P009 |
| 12 Hardness Leads (4B) | KT003084P003 | 12 Hardness Leads (2H) | KT003084P010 |
| 12 Hardness Leads (3B) | KT003084P004 | 12 Hardness Leads (3H) | KT003084P011 |
| 12 Hardness Leads (2B) | KT003084P005 | 12 Hardness Leads (4H) | KT003084P012 |
| 12 Hardness Leads (B)  | KT003084P006 | 12 Hardness Leads (5H) | KT003084P013 |
| 12 Hardness Leads (HB) | KT003084P007 | 12 Hardness Leads (6H) | KT003084P014 |

#### **Related Products**



Elcometer 501



Elcometer 3080

#### Elcometer 501 Pencil Hardness Tester

The pencil hardness test, also referred to as the Wolff-Wilborn test, uses the varying hardness values of graphite pencils to evaluate a coating's hardness.

#### Elcometer 3080 Pencil Hardness Tester

This is a simple and effective technique to evaluate the hardness of many coatings.

The pencil lead, prepared beforehand by using the special pencil sharpener and rubbing it on fine abrasive paper (400 grade), is maintained at an angle of 45° and pushed with uniform pressure on to the sample, leaving either a superficial trace or causing destruction down to the substrate.